

Composition and temperature dependent structural investigation of perovskite-type sodium-ion solid electrolyte series $\text{Na}_{1/2-x}\text{La}_{1/2-x}\text{Sr}_{2x}\text{ZrO}_3$

Thursday, 12 November 2020 17:34 (1 minute)

The development of new solid electrolytes is becoming increasingly important, e.g. in rechargeable batteries for electric vehicles, where current organic electrolytes cause major safety concerns. The ABO₃ perovskite metal oxides have shown excellent lithium and sodium ion conductivity owing to their stability and structural flexibility. This has led to the development of several perovskite-type solid electrolytes such as $\text{Li}_{3x}\text{La}_{2/3-x}\text{TiO}_3$ and $\text{Na}_{1/2-x}\text{La}_{1/2-x}\text{Sr}_{2x}\text{ZrO}_3$, which have shown high ionic conductivity.

The $\text{Na}_{1/2-x}\text{La}_{1/2-x}\text{Sr}_{2x}\text{ZrO}_3$ perovskite-type sodium-ion solid electrolyte system was recently published by Zhao et al. [1] with the $x=1/6$ member, i.e. $\text{Na}_{1/3}\text{La}_{1/3}\text{Sr}_{1/3}\text{ZrO}_3$, found to have the highest ionic conductivity. The structure was reported to adopt a cubic crystal system with the space group P213. However, this is highly unlikely as both theoretical end members of the series, $\text{Na}_{1/2}\text{La}_{1/2}\text{ZrO}_3$ and SrZrO_3 , have orthorhombic symmetry[2, 3]. Given the high ionic conductivity reported for the system, it is important to determine its structure reliable and with the best available data. Using neutron and X-ray powder diffraction data we have been able to confirm that the symmetry across the series is lowered to orthorhombic indeed. Variable temperature neutron powder diffraction data collected for the $x=1/6$ member of the system from room temperature to 1100 °C helped to identify a structural phase transition from orthorhombic to tetragonal symmetry at 800 °C.

[1] Y.Z. Zhao, Z.Y. Liu, J.X. Xu, T.F. Zhang, F. Zhang, X.G. Zhang, Synthesis and characterization of a new perovskite-type solid-state electrolyte of $\text{Na}_{1/3}\text{La}_{1/3}\text{Sr}_{1/3}\text{ZrO}_3$ for all-solid-state sodium-ion batteries, *J Alloy Compd*, 783 (2019) 219-225.

[2] B.J. Kennedy, C.J. Howard, B.C. Chakoumakos, High-temperature phase transitions in SrZrO_3 , *Phys Rev B*, 59 (1999) 4023-4027.

[3] M.C. Knapp, P.M. Woodward, Ohio State University. Department of Chemistry, Investigations into the structure and properties of ordered perovskites, layered perovskites, and defect pyrochlores, in, Ohio State University,, Columbus, Ohio, 2006, pp. xvii, 161 p.

Level of Expertise

Student

Speakers Gender

Male

Do you wish to take part in the poster slam

Yes

Primary authors: YANG, Frederick (University of Sydney); SCHMID, Siegbert; PETERSON, Vanessa (ANSTO)

Presenter: YANG, Frederick (University of Sydney)

Session Classification: Poster Session

Track Classification: Chemistry & Crystallography