Contribution ID: 63 Type: not specified

In-situ diffuse scattering experiment on stress-induced ferroelastic transformation in Ti-15Nb-2.5Zr-4Sn

Research to optimize the biocompatibility of titanium alloys for orthopaedic applications focusses on minimizing the Young's modulus of quenched, -phase (Im-3m) titanium by adjusting the concentration of -stabilizing elements. Ti-15Nb-2.5Zr-4Sn has the lowest Young's modulus yet measured in any forged titanium alloy of less than 50 GPa. This composition also possesses a controllable thermal expansion coefficient that is influenced by prior plastic deformation and it is superelastic over a very wide temperature range. There is pronounced non-linear elasticity and asymmetric response to strain, associated with the stress induced, ferroelastic transition between the bcc -phase and " (Cmcm) martensite phase. The potential to tailor these remarkable properties to specific applications, as well as further progress in superelastic alloy development require a clear microscopic understanding of the underlying physical effects. Therefore, to investigate these "pre-martensitic" phenomena and quantitatively explain the non-linear elastic responses we carried out in-situ measurement of -phase Ti-15Nb-2.5Zr-4Sn single crystals on ESRF beamline ID15B, equipped with a large position-sensitive detector and rotating load rig, that allows single-crystal x-ray scattering measurements with crystals as thick as several millimetres with simultaneous application of compressive or tensile stress.

The results give a detailed picture of the large bcc crystal as it approaches and progresses through the structural transformation. Domains of ferroelastic " and also instabilities form in response to the temperature and the direction and magnitude of the applied stress. We present these results and discuss some of the challenges of developing a quantitative interpretation of the data, an important one being how to properly treat coupling between elastic deformation and correlated structural distortions.

Primary author: Dr OBBARD, Edward (UNSW Dept. of Electrical Engineering and Telecommunications)

Co-authors: Mr WANG, Haoliang (Shenyang National Laboratory for Materials Science); Dr BURKOVSKY, Roman (St. Petersburg State Politekhnical University); Prof. HAO, Yulin (Shenyang National Laboratory for Materials Science)

Presenters: Dr OBBARD, Edward (UNSW Dept. of Electrical Engineering and Telecommunications); Prof. HAO, Yulin (Shenyang National Laboratory for Materials Science)