



Contribution ID: 98

Type: not specified

Phase Transition studies of $\text{MnSb}_{2-x}\text{Ta}_x\text{Sb}_2\text{O}_6$

Recently, the trigonal modification (sg. P321) of MnSb_2O_6 has drawn significant attention as it could be an unusual type of multiferroic behaviour and weakly polar material [1]. The magnetic susceptibility of MnSb_2O_6 shows a short range ordering below 200 K and long range ordering is observed below the Neel temperature ($T_N = 12.5$ K) resulting in an incommensurately ordered three-dimensional Heisenberg antiferromagnet [2]. MnTa_2O_6 adopts the orthorhombic MgNb_2O_6 structure type (sg. Pbcn) and it shows a monoclinic magnetic structure: $P2_1/c$ symmetry at 4.2 K ($T_N = 4.4$ K) [3]. In this solid solution, Ta could occupy the MnO interlayers and it will induce the decrease of the magnetic inter layer coupling. According to the Lab X-ray diffraction studies, a new tetragonal modification can be observed between $x = 0.2$ and 1.8. The powder can be refined as mixtures of the trigonal MnSb_2O_6 structure and a tetragonal tri-rutile modification, which is known for other MSb_2O_6 compounds, for the refinement from $x = 0.6$ to $x = 1.2$. The tri-rutile modification could be refined as the sole phase between $x = 1.4$ to 1.6. The orthorhombic MnTa_2O_6 modification could only be observed from $x = 1.7 - 2.0$. Interestingly, the tri-rutile modification has previously been described as a meta-stable modification for MnTa_2O_6 [4].

References

- [1] R. D. Johnson, K. Cao, L. C. Chapon, F. Fabrizi, N. Perks, P. Manuel, J. J. Yang, Y. S. Oh, S-W. Cheong and P. G. Radaelli, Phys. Rev. Lett. 111 (2013) 017202
- [2] J. N. Reimers and J. E. Greedan, J. Solid State Chem. 79 (1989) 263
- [3] H. Weitzel and S. Klein, Solid State Comm. 12 (1973) 113
- [4] S. Esmailzadeh and J. Grins, Solid State Sciences 4 (2002) 117

Primary author: KANG, Hyung-Been (The University of Auckland)

Co-authors: SUZUKI, Furitsu (The University of Auckland); Dr SOEHNEL, Tilo (The University of Auckland)

Presenter: KANG, Hyung-Been (The University of Auckland)